

representation only - not the item graded

GEMMOLOGICAL GRADING REPORT No. XTAN 0011

PRINS & PRINS GEMSTONE LABORATORY



Huguenot House, 66 Loop Street, Cape Town, South Africa. <u>www.prinsandprins.com</u> / Tel: 0027 21 422 Member of the S.A Jewellery Council



Identification Natural Tanzanite (TANZANIA)
Weight1.87 ct
Dimensions 6.90 x 6.87 – 4.97 mm
Shape SQUARE CUSHION
Colour Hue BLUEISH VIOLET (bV 1)
Tone DARK
Saturation INTENSE
Clarity EYE CLEAN
Cut VERY GOOD
Brilliance 70%
Final Grade PREMIER



Cushion Oval

Triangle

Round

GEMMOLOGICAL SPECIFICATIONS

Mineral Chem.Composition: Specific Gravity Hardness Refractive Index Birefringence Fluorescence Pleochroism Optic character Zoisite Ca₂A1₃O₁₂(OH) 3.35 6-7 1.691 – 1.700 .008 - .013 UV light Inert (LW/SW) Strong Trichroic Biaxial positive

Pear

This certificate is the opinion of the grader at the specific time of inspection. It is not an evaluation. The customer shall have no claim against the grader, its principal, distributor or retailer for any inaccuracies or errors contained herein PS: Most gemstones have been heated to improve their colour.

GRADER

Dr Petré Prins Ph.D Geochemistry MBA Riana Courtis G.G. (GIA) Penny Murdock A.J.P., G.G. (GIA) Daniel van Niekerk A.J.P., G.G. (GIA)

Date :

EXPLANATION OF REPORT WEIGHT: 1 carat = 200 mg = 100 pointsCOLOUR HUE: "vB" indicates that the colour is predominantly blue, while "bV" indicates that the colour is predominantly violet. bV1+ or vB1+ exceptional bV1 or vB1 = excellent bV2 or vB2 = very good bV3 or vB3 = good bV4 or vB4 = moderate bV5 or vB5 = light TONE: Describes the degree of darkness or lightness of the colour colourless -- light - medium - dark - very dark -- black SATURATION: Describes the intensity (strength) of the primary colour. very light - light - moderate - strong - intense - vivid CLARITY: indicates the amount of internal and external blemishes visible with the trained naked eye eye clean slightly included included CUT: Describes the quality of the gem's symmetry, polish and proportions very good good average BRILLIANCE : The percentage of light reflected to the eye in the stone's face-up position **FINAL GRADE** PREMIER PLUS - PREMIER - GOOD - AVERAGE - POOR