

Cushion

Oval





Pear Round

#### **GEMMOLOGICAL SPECIFICATIONS**

BERYL **Mineral** 

Be3Al2 (SiO3)6 Chem. Composition:

**Specific Gravity Hardness** 7.5-8 Refractive Index 1.544 -1.553 Birefringence 0.009 **Fluorescence** Inert Pleochroism Weak

Optic character Uni-axial positive

This certificate is the opinion of the grader at the specific time of inspection. It is not an evaluation. The customer shall have no claim against the grader, its principal, distributor or retailer for any inaccuracies or errors contained herein. Most gemstones are heated to improve their

GRADERS: Dr Petre Prins Ph.D .geochemistry MBA (Stellenbosch)

Mrs Riana Courtis. Graduate Gemmologist. (GIA) USA

Date : .....

## **AQUAMARINE**



representation only - not the item graded

# GEMMOLOGICAL GRADING REPORT

No. XAQ 033

## PRINS & PRINS GEMSTONE LABORATORY



Huguenot House,66 Loop Street, Cape Town, South Africa. www.prinsandprins.com / Tel: 0027 21 422 1090

Member of the S.A Jewellery Council

### GRADING REPORT

Identification... NATURAL AQUAMARINE ..... Origin ..... MADAGASCAR ..... Weight ...... 3.22 ct ..... Dimensions...... 10.68 x 6.95 – 5.66 mm ..... Shape ..... EMERALD CUT ..... Colour Hue ...... BLUE ..... Tone ...... LIGHT..... MODERATE ..... Saturation ..... Clarity ..... EYE CLEAN ..... Cut ...... VERY GOOD ...... Brilliance ...... 80% ..... FINAL GRADE...... PREMIER .....

#### **EXPLANATION OF REPORT**

WEIGHT: 1 carat = 200mg = 100 points

COLOUR- HUE: Describes the first impression of colour as seen with the gem facing up: eg greyish blue.

TONE: Describes the degree of darkness or lightness of the colour

colourless -- light - medium - dark - very dark -- black

SATURATION: Describes the intensity (strength) of the primary colour. very light - light - moderate - strong - intense - vivid

**CLARITY**: Indicates the amount of internal and external blemishes visible with the trained naked eye

Included - heavily slightly included eve clean included

CUT: Describes the quality of the symmetry, polish and proportions of the gemstone very good good

BRILLIANCE: The percentage of light reflected to the eye with the gemstone in a face-up position

**FINAL GRADE** 

PREMIER PLUS - PREMIER - GOOD - AVERAGE - POOR